

STATUS 100% ACRYLIC

Premium quality acrylic paint

STATUS 100% ACRYLIC is a high-quality acrylic paint for exterior use based on 100% acrylic resins. Offers high water-repellency and excellent resistance to adverse atmospheric conditions and UV radiation over time. It has strong adhesion to all kinds of old and new surface such as plaster, concrete, plaster, wood, etc. It is odorless, dries quickly and is quite friendly for the user and the environment. Its special formulation provides excellent breathability, high whiteness and resistance to frequent washing. Easy to apply, has excellent hiding power and high efficiency. It gives a beautiful matt finish.



Advantages:

- Product environmentally friendly solvent-free.
- Odorless.
- Does not contain ammonia.
- High water-repellency.
- Excellent transpiration ability of surfaces.
- Excellent resistance to sunlight.
- High resistance to adverse atmospheric conditions.
- Resistance to washing.
- Fast drying.
- Excellent coverage.
- High whiteness.
- Excellent workability.
- High performance.



TECHNICAL CHARACTERISTICS



Packaging:

Plastic containers
 • White: 0.75 lt, 3 lt, 10 lt
 • Base P, D, TR: 1lt, 3 lt, 10 lt



Color:

Available in white and thousand shades through STATUS coloring system.



Drying time:

- Touch dry
1 - 2 h
- Recoating
2 - 3 h

*Drying times refer to normal ambient conditions (25°C, 60% humidity). Drying times may differ in case of ambient temperature and humidity variations.



Dilution with water:

5-10(% v.v.)



Application:

For exterior use. Concrete, plaster, plasterboard, wood, etc.



Consumption:

15 - 17 m²/lt.



Application tools:

Brush, roller, or airless gun.



Storage:

Store the original, sealed container in a cool and dry place for 36 months of the date of production only if it has not been diluted.



V.O.C. class :

A/c Exterior walls of mineral substrate (W.B) V.O.C limit : 40gr/lt
 Maximum V.O.C of product ready to use product: 39 gr/lt.

FIELDS OF APPLICATION

Suitable for external application of new or old painted stone work.

Applied on concrete, plaster, plasterboard, wood, etc.

SUBSTRATE PREPARATION

Before applying, ensure that the surface is clean, dry, robust and free from dust, mold and grease. Remove damaged, or peeling old paint. Where putting is required, use the STATUS 100% ACRYLIC PUTTY and after drying, sand with sandpaper and dust thoroughly. If there are large cracks, use the ready-to-use white stucco STATUS ONE COVER, fill the cracks applying just one coat without sanding. On new surfaces, prime with STATUS ACRYLIC PRIMER, or STATUS AQUADUR before the application. In the case of fresh plaster or cement, let the surface dry thoroughly for at least one month before painting. For plasterboard and for the repainting of hydro colored surfaces (with lime or glue) or soiled surfaces (nicotine, soot from heaters, soot, fumes, coffee, juice, graffiti, inks, markers, mildew, mold, moisture, oil, etc.), prime with STATUS DUR before the application. Do not ever paint surfaces that may contain moisture. First make sure that the cause of the moisture stopped and that the surface is completely dry.

APPLICATION

Stir well the contents of the container before use, dilute properly and apply 1-2 coats of paint. Apply the second coat at least 2-3 hours after the first. After the application close the container tightly to maintain the paint in good condition for future use. You can store undiluted paint in a tightly sealed container for extended periods of time without affecting the quality of the product. The paint surface is recommended not to be washed for the first 20 to 30 days after the application. On new surfaces of plaster or concrete paint after 30-40 days.

TOOL CLEANING

Immediately after use, drain excess paint thoroughly into the container and clean tools using warm soapy water. Do not dispose of washing waste water into the aquifer groundwater.

COMMENTS

More information regarding the reasons why this product was given the EU Ecolabel can be found on the EU website:

<http://ec.europa.eu/environment/ecolabel/>

PRECAUTIONS

For information on the safe use, storage and disposal of the product read the information on the label and in the most recent Product Safety Data Sheet. The Product Safety Data Sheet is available at the professionals' request. Remaining paint should not be disposed of with household waste. You should seek advice from local authorities regarding the disposal and collection of waste.

[Poisons Information Call Center 210 77.93.777](tel:2107793777)

APPLICATION TEMPERATURE

During the application temperatures should be at 5-35°C and <80% RH. Do not start the application before rain. Ensure the surface is protected from direct solar radiation throughout the process. Adverse conditions during or immediately after application may affect the final properties of the product.

Technical characteristics	Units	Standard	Value
Viscosity	cP	EN ISO 2555	12000 - 16000
Density	g/ml	EN ISO 2811-1	1.44 ± 0.03
- WHITE			1.44 ± 0.03
- BASE P			1.43 ± 0.03
- BASE D			1.42 ± 0.03
- BASE TR			
pH		ISO 976	8.0 - 9.0
Gloss (60° C)	%	EN ISO 2813	≤3
Dilution	%		5 - 10
Recoating time	h		2 – 3
Drying time	h		1 - 2

*Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative humidity 50% and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now know-how and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.

Version Δ: 01/10/2024