

STATUS ALL WEATHER

Elastomeric waterproof façade paint



STATUS ALL WEATHER is the result of extensive research and exhaustive testing under the harshest climatic conditions. This is an innovative elastomeric paint that coats and simultaneously insulates exterior walls, ensuring absolute protection from moisture, chemical contaminants and concrete carbonation, while offering exceptional durability. Its special formula creates an elastic membrane, which covers all hairline cracks follows the surface's shrinkages and expansions and thanks to the built-in ultraviolet radiation filters remains flexible without cracking, or peeling. It is the ideal solution for painting and protecting buildings, mainly in urban, mountainous, and industrial areas. It has the ability to prevent the formation of mold, while exhibiting a reduced tendency for the retention of multiple pollutants due to UV crosslinking. It is easy to apply, has excellent coverage and high performance.












Advantages:

- Solvent-free environmentally- friendly product.
- Odorless.
- High elasticity.
- Provides excellent surface perspiration.
- Extremely resistant to sunlight.
- Extremely resistant to chemical pollutants.
- Exceptional protection against concrete carbonation.
- High resistant to adverse atmospheric conditions(rain, frost, heat) .
- Wash resistant.
- Excellent coverage.
- Highly workable.
- Great Performance
- Technology against mildew.



TECHNICAL CHARACTERISTICS

 <p>Packaging: Plastic containers • White, Base P, D, TR : 3 lt, 10 lt</p>	 <p>Color: Available in white and thousands of shades through STATUS paint system.</p>	 <p>Drying time:</p> <ul style="list-style-type: none"> • Touch dry 2-3 h • Recoating 4-6 h 	<p>*Drying times refer to normal ambient conditions (25°C, 60% humidity). Drying times may differ in case of ambient temperature and humidity variations.</p>
 <p>Dilution with water: 5-10 (% v.v.)</p>	 <p>Application: For exterior use. Plaster, fair-face concrete, plasterboards, wood, etc.</p>	 <p>Consumption: 11-13 m²/lt</p>	
 <p>Application tools: Brush, roller, or airless gun.</p>	 <p>Storage: Store in tightly closed container for 36 months of the date of production only if it has not been thinned. Store in a cool and dry place.</p>	 <p>V.O.C. class : Exterior walls of mineral substrate (W.B) V.O.C limit: 40 gr/lt Maximum V.O.C of product ready to use: 39 gr/lt</p>	

FIELDS OF APPLICATION

Suitable for the exterior application on new or old painted masonry. Applied on all kinds of old and new surfaces such as plaster, fair-face concrete, plaster-boards, wood, etc. Finally, it is applied to surfaces subject to frequent washing.

SUBSTRATE PREPARATION

Before use, ensure that the surface is clean, dry, robust and free from dust, mold and grease. Remove damaged, or peeling old paint. Where puttying is required, use the STATUS 100% ACRYLIC STUCCO and after drying, sand the surface down and dust well. If there are large cracks, use ready-to-use light white Stucco STATUS ONE COVER, to fill the cracks applying just one coat without sanding. New surfaces, should be primed with STATUS ACRYLIC PRIMER, STATUS AQUADUR or GLX 292 FLEX PRIM. For surfaces covered in fresh plaster or cement, allow the surfaces to dry thoroughly for at least 1 month before painting. For plaster-boards and recoating water-base colored surfaces (with white-wash or adhesive) or soiled surfaces (nicotine, soot from heaters, soot, fumes, coffee, juice, graffiti, inks, markers, mildew, mold, moisture, oil, etc.), prime first with STATUS DUR. DO not paint surfaces that may contain moisture. First make sure that the cause of the moisture has stopped and that the surface is completely dry.

APPLICATION

Mix well before use, dilute properly and apply 1-2 coats of paint. Allow at least 4-6 hours before applying the second coat. Close the container tightly after use to keep the paint in good condition for future use. You can store undiluted paint in a tightly sealed container for extended periods of time without affecting the quality of the product. Allow 20-30 days before washing painted surfaces and 30-40 days before washing freshly painted new plaster or concrete surfaces. The painted surfaces can be cleaned using a soft sponge with water. If stains persist, use a mild, colorless detergent.

APPLICATION TEMPERATURE

During the application temperatures should be at 5-35°C and <80% RH. Do not start the application before rain. Ensure the surface is protected from direct solar radiation throughout the process. Adverse conditions during or immediately after application may affect the final properties of the product.

TOOL CLEANING

Immediately after use, drain excess paint thoroughly into the container and clean tools using warm soapy water. Do not dispose of washing waste water into the aquifer groundwater.

PRECAUTIONS

For information on the safe use, storage and disposal of the product read the information on the label and in the most recent Product Safety Data Sheet. The Product Safety Data Sheet is available at the professionals' request. Remaining paint should not be disposed of with household waste. You should seek advice from local authorities regarding the disposal and collection of waste.

[Poisons Information Call Center 210 77.93.777](tel:2107793777)

Technical characteristics	Units	Standard	Value
Viscosity	cP	EN ISO 2555	12000 – 16000
Density			
- WHITE	g/mL	EN ISO 2811-1	1.48 ± 0.03
- BASE P			1.48 ± 0.03
- BASE D			1.45 ± 0.03
- BASE TR			1.45 ± 0.03
pH		ISO 976	8.0 – 9.0
Gloss (60° C)	%	EN ISO 2813	≤6
Dilution	%	-	5 – 10
Recoating time	h		4 – 6
Drying time	h		2 - 3

*Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative humidity 50% and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now know-how and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.

Version D: 01/10/2024