

STATUS METALLIC

Water based metallized paint



STATUS METALLIC is a decorative rust preventive water-based paint ideal for all indoor or outdoor metal surfaces as well as for walls, wood, rails, banisters, doors etc. Its advanced composition allows application directly on rusty surfaces, where it blocks rust and prevents its reappearance. Exceptional resistance, very good spreading, strong adhesion and anticorrosive protection. It delivers a matt, textured, and highly durable finish, with long-lasting color stability.



Advantages:

- Gel formula (no dripping).
- No stains.
- Directly onto the rust.
- High antirust protection.
- Excellent metallized finish.
- Very good spreading.
- High resistance.
- Strong adhesion.
- Anticorrosive protection.



TECHNICAL CHARACTERISTICS



Packaging:

- Plastic containers
- 650 ml



Color:

Available in Silver and 5 additional shades through THRAKON's tinting system



Drying:

- To the touch
1 - 2 h
- Recoating
12 h

*Drying times refer to normal ambient conditions (25°C, 60% humidity). Drying times may differ in case of ambient temperature and humidity variations.



Dilution with water:

- Ready to use with brush or roller
- 10-15 (% v/v) for application with gun



Application:

For exterior and interior use. Suitable for all kinds of metals as well as walls, wood, rails, banisters, doors etc.



Consumption:

7-9 m²/lt



Application tools:

Brush, roller or airless gun.



Storage:

After application close the container tightly to preserve in good condition for future use. It can be stored in tightly closed containers for a long time as long as it has not been diluted. Store in cool and dry places and protect from sun and frost.



V.O.C. class :

Special 1-component plasters and renders (W.B). V.O.C. limit: 140 gr/lt. Maximum V.O.C. of product ready to use: 135 gr/lt.

FIELDS OF APPLICATION

Suitable for all outdoor and indoor metal surfaces as well as for walls, wood, rails, banisters, doors etc.

SUBSTRATE PREPARATION

The surface should necessarily be rigid, dry and free from dust, grease or rust for good adhesion. Remove all loose, peeled old paints or rust. Surfaces previously painted with oil paint should be sanded and wiped well. New metal surfaces should be cleaned with acetone or LS-735 NITRO SOLVENT. For maximum protection the surfaces should be primed with STATUS POLYPRIMER ecological water-soluble primer. STATUS METALLIC can be applied on unprimed metals as long as the film is at least 120 µm thick (2 layers). On non-iron metal surfaces (galvanized, aluminum etc.) first apply WASH PRIMER and then apply 2 layers of STATUS METALLIC.

APPLICATION

Stir well the content of the container before use, and apply with brush 2 layers of STATUS METALLIC. The second layer should be applied at least 12 hours after the first. In case of gun application, apply 3 layers so that the final film is at least 120 µm. For perfect finish on large surfaces apply with a gun. Apply thick layers of the product to secure increased protection against rust. Pay particular attention when fully covering difficult points, such as corners and hollows in order to prevent any possible penetration of humidity.

APPLICATION TEMPERATURE

During the application temperatures should be at 5°-35°C and <80% RH. Do not start the application before rain. Ensure the surface is protected from direct solar radiation throughout the process. Adverse conditions during or immediately after application may affect the final properties of the product.

TOOL CLEANING

Immediately after use, empty all the paint into the container and clean the tools with hot water and soap. Do not empty washings into the groundwater.

PRECAUTIONS

For information on the safe use, storage and disposal of the product read the information on the label and in the most recent Product Safety Data Sheet. The Product Safety Data Sheet is available at the professionals' request. Remaining paint should not be disposed of with household waste. You should seek advice from local authorities regarding the disposal and collection of waste.

[Poisons Information Call Center 210 77.93.777](tel:2107793777)

| Technical characteristics | Units | Standard | Value |
|---------------------------|-------|-----------------------|--------------|
| Viscosity | sec | ASTM D 5125, ISO 2431 | 120 – 180 |
| Density | g/mL | EN ISO 2811-1 | 1.43 ± 0.03 |
| Dilution | | | |
| - Brush, roller | % | - | Ready to use |
| - Gun | | | 10 – 15 |
| Recoating time | h | - | 12 |
| Drying time | h | - | 1 – 2 |

*Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative humidity 50% and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now know-how and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.

Version B: 26/07/2025