

STATUS RUSTBLOCK HAMMER

Hammered Finish Anticorrosive Enamel



STATUS RUSTBLOCK HAMMER is an anticorrosive solvent-based enamel, specifically formulated for direct application onto rusted surfaces. Its advanced composition offers robust protection for aged metal substrates, ensuring excellent adhesion and smooth leveling. The resulting finish resembles wrought metal, combining exceptional durability with shades that remain unchanged over time.



Advantages:

- Excellent corrosion protection.
- No red lead or alternative rust primers are required.
- Delivers a high gloss finish, enhanced hardness, and strong resistance to harsh weather conditions and mechanical impact.
- Strong adhesion.
- Excellent leveling and workup.
- Excellent coverage.
- High performance.



TECHNICAL CHARACTERISTICS



Packaging:

Metallic containers
• 750 ml
• 2,5 lt



Color:

Available in 5 ready-made shades.



Drying:

- To the touch
1.5 - 2 h
- Recoating
24 h

*Drying times refer to normal ambient conditions (25°C, 60% humidity). Drying times may differ in case of ambient temperature and humidity variations.



Application:

For exterior and interior use. Suitable for all kinds and metals such as doors, railings, metal handrails, elevators etc.



Consumption:

6-8 m²/lt



Application tools:

Brush, roller or airless gun.



Storage:

In the original sealed container, in dry places at temperatures between +5° C and +35° C for 24 months after the production date.



V.O.C. class :

A/c Coatings & exterior walls of mineral substrate (S.B). V.O.C. limit: 500 gr/lt.
Maximum V.O.C. of product ready to use: 499 gr/lt
Maximum thinning: 10% v/v.

FIELDS OF APPLICATION

Suitable for paint and rust protection of all kinds of new and old metal surfaces, such as doors, railings, metal handrails, elevators etc.

SUBSTRATE PREPARATION

The surface should necessarily be rigid, dry and free from dust, grease or rust for good adhesion. Remove all loose or peeled old paints. Surfaces previously painted with oil paint should be sanded and wiped well. In non-ferrous metal surfaces (galvanized, aluminum etc.) first apply the WASH PRIMER and then the STATUS BUILDING PRIMER. In addition, to ensure maximum corrosion protection especially in aggressive environments such as coastal and industrial areas or northern sides, first paint with STATUS RUST PRIMER or STATUS MINIO.

APPLICATION

Stir well the content of the container before use, dilute properly and apply the product, in 2 thick layers with particular attention to the full coverage of difficult points, such as corners, recesses etc. to avoid possible ingress of moisture causing oxidation. To ensure maximum protection from rust, the film thickness should be at least 100-120 μ m. Then close well the container to maintain in good condition for future use. Can be stored in a tightly closed container, without any problem for a long time.

APPLICATION TEMPERATURE

During the application temperatures should be at 5°-35°C and <80% RH. Do not start the application before rain. Ensure the surface is protected from direct solar radiation throughout the process. Adverse conditions during or immediately after application may affect the final properties of the product.

TOOL CLEANING

Immediately after use, clean the brush, or roll with WHITE SPIRIT and then with hot water and detergent. Clean the spray gun with acetone, or LS-735 NITRO SOLVENT UNIVERSAL. Do not empty washings into the groundwater.

PRECAUTIONS

For information on the safe use, storage and disposal of the product read the information on the label and in the most recent Product Safety Data Sheet. The Product Safety Data Sheet is available at the professionals' request. Remaining paint should not be disposed of with household waste. You should seek advice from local authorities regarding the disposal and collection of waste.

[Poisons Information Call Center 210 77.93.777](tel:2107793777)

Technical characteristics	Units	Standard	Value
Viscosity	sec	ASTM D 5125, ISO 2431	120 – 210
Density	g/ml	EN ISO 2811-1	0.96 ± 0.03
Dilution			
- Application with brush or roller	%	-	Up to 5% with white spirit
- Application with gun			Up to 5% with LS-703 solvent
Recoating time	h	-	24
Drying time	h		1.5 - 2

*Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative humidity 50% and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now know-how and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.

Version B: 26/07/2025