

STATUS WATER BASED COATING

Water based coating

STATUS water based coating is a water-soluble paint for interior use. It is suitable for stairwells, storages, kitchen ceilings, bathrooms, bedrooms and surfaces that do not require washing. It is easy to apply, has excellent coverage, spreading and whiteness. It has excellent transpiration ability thus preventing the concentration of vapor. It has low drying times and can be recoated very quickly.



Advantages:

- Environmentally friendly solvent-free.
- Odorless.
- Does not contain ammonia.
- Excellent transpiration ability of surfaces.
- Excellent coverage.
- High whiteness.
- Excellent workability.
- Wonderful spreading.
- Economic solution for professionals.



TECHNICAL CHARACTERISTICS

Packaging:

Plastic containers
• 3 lt
• 9 lt

Color:

Available in white.

Application:

For interior use. Stairwells, storages, kitchen ceilings, bathrooms, bedrooms etc.

Drying time:

- Touch dry
1 - 2 h
- Recoating
3 - 4 h

*Drying times refer to normal ambient conditions (25°C, 60% humidity). Drying times may differ in case of ambient temperature and humidity variations.

Dilution with water:

5 - 10 (% v.v.)

Consumption:

10-12 m²/lt depending on the texture and porosity of the surface

Storage:

Store the original, sealed containers in dry environment at temperatures between +5°C and +35°C for 12 months from production date.

Application tools:

Brush, roller, or airless gun.

V.O.C. class :

A/a Interior matt walls and ceilings (Gloss ≤25 at 60°) (W.B) V.O.C limit: 30 gr/lt.
Minimum thinning with water: 10% v/v.
Maximum V.O.C of product ready to use: 25 gr/lt.

FIELDS OF APPLICATION

Suitable for interior application on new surfaces or surfaces already painted with water based coatings. Suitable for kitchen ceilings, bathrooms, bedrooms, stairwells, storages etc.

SUBSTRATE PREPARATION

Before applying, ensure that the surface is clean, dry, robust and free from dust, mold and grease. Remove damaged, or peeling old paint. Where putting is required, use the STATUS 100% ACRYLIC PUTTY and after drying, sand the surface and clean the dust thoroughly. If there are large cracks, use the ready-to-use white stucco STATUS ONE COVER, fill the cracks applying just one coat without sanding. On new surfaces, prime with STATUS ACRYLIC PRIMER, STATUS AQUADUR or FLEX PRIM GLX 292 before the application. In the case of fresh plaster or cement, let the surface dry thoroughly for at least one month before painting. On gypsum boards or for repainting water painted surfaces (with lime or glue) or soiled surfaces (nicotine, soot from heaters, soot, fumes, coffee, juice, graffiti, inks, markers, mildew, mould, moisture, oil etc.) prime first with STATUS AQUADUR.

APPLICATION

Mix well before use, dilute properly and apply 1-2 coats of paint. Allow at least 3-4 hours before applying the second coat. Close the container tightly after use to keep the paint in good condition for future use. You can store undiluted paint in a tightly sealed container for extended periods of time without affecting the quality of the product. Allow 30-40 days before painting new plaster or concrete surfaces.

APPLICATION TEMPERATURE

During the application temperatures should be at 5°-35°C and <80% RH. Do not start the application before rain. Ensure the surface is protected from direct solar radiation throughout the process. Adverse conditions during or immediately after application may affect the final properties of the product.

TOOL CLEANING

Immediately after use, drain excess paint thoroughly into the container and clean tools using warm soapy water. Do not dispose of washing waste water into the aquifer groundwater.

PRECAUTIONS

For information on the safe use, storage and disposal of the product read the information on the label and in the most recent Product Safety Data Sheet. The Product Safety Data Sheet is available at the professionals' request. Remaining paint should not be disposed of with household waste. You should seek advice from local authorities regarding the disposal and collection of waste.

[Poisons Information Call Center 210 77.93.777](tel:2107793777)

Technical characteristics	Units	Standard	Value
Viscosity	cP	EN ISO 2555	16000 – 20000
Density	g/ml	EN ISO 2811-1	1.56 ± 0.03
pH		ISO 976	8.0 – 9.0
Gloss (60° C)	%	EN ISO 2813	≤2
Dilution	%		5 – 10
Recoating time	h		3 – 4
Drying time	h		1 – 2

*Note: The measurements were taken in laboratory environment under a temperature of +23°C, Relative humidity 50% and without ventilation. It is possible for them to vary depending on the conditions prevailing at the worksite, such as temperature, humidity, ventilation, absorbability of the substrate.

The technical information and instructions contained in the present brochure and referring to the application and end use of Thrakon products are based on the up to now know-how and experience of the Company with regards to the products and are provided in good faith as long as such products are stored, used and applied as per Thrakon recommendations. Due to the inability, on our part, to directly inspect the conditions prevailing at the worksite as well as the application procedures of the product, the Company does not provide any guarantee with regards to the adequacy of its products for specific purpose while the Company shall not bear any legal responsibility based on the information stated in the present brochure or any other written, oral, or otherwise provided recommendations and instructions. The users of the products are advised to perform a limited surface testing of the products adequacy for the eventual application and use intentions. Thrakon reserves the right to modify the features of its products without prior notification. All orders shall be approved only following acceptance of the above and under the eventual Commercial Policy terms of the Company. The issuance of the present brochure voids any prior version.

Version B: 24/11/2024